

CHARLES PARSONS

Textiles

Est. 1915

1400F Formfuse

DESCRIPTION Non-Woven Fusible Interlining

APPLICATION Light to medium weight iron on fusible non-woven ideal for small parts such as collars and cuffs, waistbands and craft projects.

COLOURS Charcoal & White

WEIGHT 36 GSM

WIDTH 100cm

ROLL LENGTH 50m per roll.

COMPOSITION 47% Polyester/ 22% Polyethylene/ 19% Acrylic/ 12% Rayon

COATING Polyethylene – low density

FUSING CONDITIONS
Dial Temp: 130 – 140 degrees Celsius
Glueline Temp: 120 – 130 degrees Celsius
Pressure: 20 – 30N/cm 2-3 Bar
Time: 10-12 seconds

Application advice for using domestic iron. For best results:

Using a pressing cloth is a great idea as it protects the interfacing, fabric and the iron

Position the glue/resin side to the wrong side of the fabric to be interfaced. Best to use dry heat and avoid steam where possible. For the heat setting use the "wool" setting on a domestic iron. Work from the center out lifting and lowering the iron applying as much pressure as possible for 10 – 12 seconds to secure a good bond.

Let the fused area cool undisturbed before using. Best to try a smaller sample before commencing major work. Generally, with fusible interlinings, fabrics with uneven surface may require more pressure and thicker fabrics require more heat. Refer to garment pattern for further cutting information.

CARE INSTRUCTIONS Washable up to 40 degrees Celsius

The information contained in this performance specification sheet is subject to change without notice and remains the property of Charles Parsons and Co. It shall not be reproduced in whole or part, nor provided to any third parties without the written authorisation of Charles Parsons and Co. Charles Parsons and Co makes no warranty of any kind with regard to this technical specification, including but not limited to, the implied warranties of merchantability and fitness for a particular purpose. Charles Parsons and Co shall not be liable for incidental or consequential damages in connection with the supply, performance or use of this fabric. The previous conditions are only a guide.
A preliminary trial is recommended before using the product in production