

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT ISO 105 B02			RUBBING ISO X 10			WASHING ISO 500c			WATER ISO 105 E01			PERSPIRATION ISO 105 E04		
	C.C	Dry	Wet	S.Co	S.Pa	S.PI	C.C	S.Co	S.Pa	S.PI	C.C	S.Co	S.Pa	S.PI	
STONE GREY	4-5	4	3-4	4	3	4	4-5	4-5	3-4	4-5	4-5	4-5	4	4-5	
MERCURY	4	3	3-4	4	3	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	

- C.C: Colour Change.
- S.Co: Staining on Cotton.
- S.Pa: Staining on Nylon.
- S.PI: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		