

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	LIGHT AS2001.4.21 60HRS	RUBBING AS2001.4.3		WASHING 40oc AS2001.4.15 TEST J2				WATER AS2001.4-E01				PERSPIRATION AS2001.4-E04			
		Dry	Wet	C.C	S.Co	S.Pa	S.PI	C.C	S.Co	S.Pa	S.PI	C.C	S.Co	S.Pa	S.PI
WHITE	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
PEWTER	5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4	4-5	4-5	4-5	4	4-5
HUNTER	5-6	4	4	4-5	4	3	4	4-5	4-5	3-4	4-5	4-5	4-5	3-4	4-5
BLACK	5-6	4-5	4	4-5	4	3	4-5	4-5	4	3-4	4-5	4-5	4	4	4-5
ESPRESSO	5-6	4-5	4	4-5	4	3	4	4-5	4-5	4	4-5	4-5	4-5	4	4-5
NAVY	5-6	4	4	4-5	4	4	4	4-5	4	3-4	4	4-5	4	3-4	4
IVORY	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
OXFORD	5-6	4-5	4	4-5	4-5	4	4-5	4-5	4	3-4	4	4-5	4	4	4
ALMOND	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
ELM	5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5

- C.C: Colour Change.
- S.Co: Staining on Cotton.
- S.Pa: Staining on Nylon.
- S.PI: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		